

Technical Data

JOTUN WOODSHIELD VARNISH



Product description

Jotun WoodShield Varnish is based on a special alkyd oil suitable for interior and exterior wooden surfaces. It is hard wearing and protects against knocks and spills. Gives an exclusive durable finish.

Recommended use

For interior and exterior on all kinds of untreated hardwood, softwood, plywood, chip board, etc. or as a topcoat in system with Jotun Woodshield Preserver and Jotun Woodshield stain. Can also be used on wood previously treated with other wood protections. For exterior, Jotun Woodshield Varnish Clear must only be used in system with colored Jotun Woodshield Stain.

Film thickness and spreading rate

	Minimum	Maximum	Typical
Film thickness, dry (µm)	30	40	35
Film thickness, wet (µm)	70	95	80
Theoretical spreading rate (m ² /l)	14	10.5	12

Physical properties

Colour According to colour card and Multicolor tinting system.

Solids (vol %)* 42 ± 2

Flash point 36°C ± 2 (Setaflash)

*Measured according to ISO 3233:1998 (E)

Surface preparation

The Surface must be clean, dry, knots must be degreased with Jotun Lacquer Thinner and exposed wood must be sanded to reach a sound surface.

Other surfaces

The coating may be used on other substrates. Please contact your local Jotun office for more information.

Condition during application

The temperature of the substrate should be min. 10°C and min. 3°C above the dew point of the air, temperature and relative humidity measured in the vicinity of the substrate.

Application methods

Brush Recommended.

Roller Recommended.

Application data

Mixing ratio (volume)
Thinner/Cleaner

Single pack.
Jotun Thinner No. 2

Drying time

Drying times are generally related to air circulation, temperature, film thickness and number of coats, and will be affected correspondingly. The figures given in the table are typical with:

- * Good ventilation (Outdoor exposure or free circulation of air)
- * Typical film thickness
- * One coat on top of inert substrate

Substrate temperature	10°C	23°C	40°C
Surface dry	10 h	5 h	3 h
Through dry	48 h	24 h	18 h
Dry to recoat, minimum ¹	24 h	12 h	8 h
Dry to recoat, maximum ^{2,3}			

1. Recommended data given for recoating with the same generic type of paint.
2. In case of multi-coat application, drying times will be influenced by the number and sequence and by the total thickness of previous coats applied – reference is made to the corresponding system data sheet.
3. The surface should be dry and free from any contamination prior to application of the subsequent coat.

The given data must be considered as guidelines only. The actual drying time/times before recoating may be shorter or longer, depending on film thickness, ventilation, humidity, underlying paint system, requirement for early handling and mechanical strength etc. A complete system can be described on a system sheet, where all parameters and special conditions could be included.

Typical paint system

INTERIOR

System 1

Jotun Woodshield Stain*	2 coats
Jotun Woodshield Varnish Clear	1 coat

System 2

Jotun Woodshield Varnish (Clear or Tinted)*	2 coats
---	---------

* if anti-termite protection is required, use Jotun Woodpreserver as the first coat

EXTERIOR

System 1

Jotun Wood Preserver	1 coat
Jotun Woodshield Stain (tinted)	2 coats
Jotun Woodshield Varnish Clear	1 coat

System 2

Jotun Wood Preserver	1 coat
Jotun Woodshield Varnish in colour	2 coats

Other systems may be specified, depending on area of use

Storage

The product must be stored in accordance with national regulations. The product must be kept in a cool and well-ventilated place, protected from heat and direct sunlight. Containers must be kept tightly closed.

Handling

Handle with care. Stir well before use.

Packing size

0.9 L and 3.9 L.

Packing may vary from country to country according to local requirements.

Health and safety

Please observe the precautionary notices displayed on the container. Use under well ventilated conditions. Avoid skin contact. Spillage on the skin should immediately be removed with suitable cleanser, soap and water. Eyes should be well flushed with water and medical attention sought immediately.

For detailed information on the health and safety hazards and precautions for use of this product, we refer to the Material Safety Data Sheet.

DISCLAIMER

The information in this data sheet is given to the best of our knowledge based on laboratory testing and practical experience. However, as the product is often used under conditions beyond our control, we cannot guarantee anything but the quality of the product itself. We reserve the right to change the given data without notice.

Head Office & Nordic

Jotun Paints
P.O. Box 2021
N-3248 Sandefjord
Norway
Phone +47 33 45 70 00
Fax +47 33 46 46 13

Europe

Jotun Paints (Europe) Ltd.
Stather Road, Flixborough
North Lincolnshire DN15 8RR
United Kingdom
Phone +44 172 44 00 000
Fax +44 172 44 00 100

Middle East

Jotun U.A.E Ltd. LLC.
Al Quoz Industrial Area
P.O Box 3671
Dubai U.A.E
Phone +971 4 3 39 50 00
Fax +971 4 3 38 06 66

South East Asia

Jotun (Singapore) Pte. Ltd.
No 11-15, Sixth Lok Yang
Road
Jurong
Singapore 628 111
Phone +65 6265 4711
Fax +65 6265 7484

Jotun is a World Wide company with factories, sales offices and stocks in more than 50 countries. For your nearest local Jotun address please contact the nearest regional office or visit our website at www.jotun.com

ISSUED 18 NOVEMBER 2002 BY JOTUN PAINTS
THIS DATA SHEET SUPERSEDES THOSE PREVIOUSLY ISSUED